

INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

(51) International Patent Classification ⁷ :

D21C 9/10

A1

(11) International Publication Number:

WO 00/53844

(43) International Publication Date: 14 September 2000 (14.09.00)

(21) International Application Number: PCT/SE00/00452


(22) International Filing Date: 7 March 2000 (07.03.00)

(30) Priority Data:
9900816-1 8 March 1999 (08.03.99) SE(71) Applicant (for all designated States except US): HOLMEN
AKTIEBOLAG [SE/SE]; Box 5407, S-114 84 Stockholm
(SE).

(72) Inventors; and

(75) Inventors/Applicants (for US only): ZHANG, Yijing [SE/SE];
Björnvägen 22, S-761 41 Norrtälje (SE). AXELFELT,
Micael [SE/SE]; Postlåda 2600, S-742 95 Hargshamn (SE).
BENGTTSSON, Sverker [SE/SE]; Tulkavägen 69, S-763
43 Hallstavik (SE). WANCKE STÅHL, Charlotte [SE/SE];
Hägemäsvägen 8, 9 tr, S-183 66 Täby (SE). ÖSTERBERG,
Johanna [SE/SE]; Ymergatan 13C, S-753 23 Uppsala (SE).(74) Agent: JONSSON, Per-Erik; Holmen Aktiebolag, S-891 80
Örnsköldsvik (SE).(81) Designated States: CA, JP, US, European patent (AT, BE, CH,
CY, DE, DK, ES, FI, FR, GB, GR, IE, IT, LU, MC, NL,
PT, SE).**Published***With international search report.**Before the expiration of the time limit for amending the
claims and to be republished in the event of the receipt of
amendments.*

(54) Title: METHOD FOR MANUFACTURING BLEACHED MECHANICAL AND CHEMITHERMOMECHANICAL PULP



(57) Abstract

There is a need to enhance the bleaching effect achieved when bleaching mechanical and chemithermomechanical pulp with a reductive bleaching agent. This can be achieved with the present invention, which relates to a method for manufacturing bleached mechanical and chemithermomechanical pulp including that lignocellulose material, preferably wood in chip form, is caused to pass through at least one preheater or through a chemical treatment system, a steam separator and a refiner where the lignocellulose material is converted into a pulp suspension which, after steam separation, is passed at least to a storage vessel (latency chest) and to a screening department, from which the major part of the pulp suspension is taken out as a substantially finished product or is taken out and passed to further treatment steps. The reductive bleaching agent is added to the advancing pulp suspension without the use of a bleaching tower or the like. The method is characterized by adding the bleaching agent at a location downstream of the refiner and upstream of the screening department, and by bleaching the pulp under the given drastic condition from the aspect of temperature and the given minimized oxygen access at said location and immediately downstream of said location.